SUPPLIERS OF MINERALS, ORES AND FERRO-ALLOYS TO THE FOUNDRY, REFRACTORY AND METALLURGICAL INDUSTRIES

PRODUCT DATA SHEET

CHROME FLOUR

Chemical Analysis	*Typicals*
Cr_2O_3	46%
SiO_2	1%
Fe	20,23%
FeO	26,50%
Al_2O_3	15,17%
CaO	0,18%
MgO	9,22%
TiO_2	0,69%
V_2O_5	0,34%

Following grades also available:

44% Cr_2O_3
46% Cr_2O_3

Sizes

For use in the Refractories and Glass and Ceramics Industries as well as for coatings in the Foundry Industry.

Ref: IM59A

Information above is given in good faith as accurate but not guaranteed to be a specification. No guarantee is given or implied. Users should conduct tests to determine suitability for any specific purpose

PO Box 782053, Sandton 2146, South Africa
4 Arlington Road, Bryanston 2191, Gauteng, South Africa
Phones : +27 11 706 0322 **Fax**: +27 11 463 2475
shipping@intermetmin.co.za www.intermetmin.co.za